



Interior Applications

Product	Polymer NVM	pH	MFFT (°C)	Tg (°C)	Coalescing Solvent (on binder nvm)	Description
WALL & TRIM GLOSS ENAMELS						
EPS 2520	45.0	7.0 - 8.0	30	15	15% Texanol	Superior block resistance, adhesion and gloss development. For high-performance interior gloss enamels and light-duty Industrial Maintenance applications.
STAIN-BLOCKING PRIMERS						
EPS 2553	45.0	7.5 - 8.5	40	15	15 - 18% Texanol	Excellent adhesion, ink and tannin stain-blocking, efflorescence resistance and corrosion resistance. Balance of hardness and flexibility offers good sandability.
INTERIOR WOOD FINISHES						
EPS 2545	30.0	9.0 - 10.0	1	4	No coalescing solvent needed	Acrylic dispersion with excellent penetration and re-solubility properties for interior stain applications. Also useful for alkali strippable temporary coatings.
EPS 2538	40.0	9.0 - 10.0	56	30	15% DPnB	Room temperature self-crosslinking emulsion for all clear applications on wood, plastic and cementitious substrates where hardness development is demanded.
EPS 2539	40.0	6.5 - 7.5	57	30	15 - 20% DPnB	Room temperature self-crosslinking emulsion for all clear applications on wood, plastic and cementitious substrates where minimal color change is required.
EPS 4203	38.5	8.0 - 9.0	na	na	10 - 15% DPnB	Room temperature self-crosslinking polyurethane dispersion (PUD) for wood and plastic substrates. This product is not on the Canadian DSL.
EPS 4213	33.0	7.7 - 8.3	na	na	none required	Oxidizing polyurethane dispersion offering fast dry, hardness development and chemical resistance for wood flooring.

EPS low VOC technology is protected under U.S. patent number 6,762,230. Other patents are pending

Questions? Call EPS Technical Service @ 1-800-601-8111

(4/08)

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option