



rev.04-21-08

## Urethane Resins for Wood Flooring & Clear Finishes

### HIGH SOLIDS OIL MODIFIED URETHANES

PRODUCT	NVM	WPG	OIL TYPE	SOLVENT	ACID #	VISC.	VISC. Reduced	COLOR	Sward Hardness	NOTES
EPS 4810	75.0	7.85	Soya	LAMS	2 max	V-X	F-H @ 65%	7 max	14	<ul style="list-style-type: none"><li>• Light color</li><li>• Good thru dry.</li><li>• Blend with 60% solids to increase hardness.</li></ul>
EPS 4854	70.0	7.87	Mixed	LAMS	2 max	S-U	N/A	6 max	25	<ul style="list-style-type: none"><li>• Improved thru dry and hardness development.</li><li>• Low viscosity.</li><li>• High gloss thru flat.</li></ul>

LAMS = Low Aromatic (<1%), Rule 66, Mineral Spirits

**Questions? Call EPS Technical Service @ 1-800-601-8111**

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. **UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES.** Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.