



Urethane Resins for Wood Flooring & Clear Finishes

CONVENTIONAL SOLIDS OIL MODIFIED URETHANES AND URALKYDS

PRODUCT	NVM	WP G	OIL TYPE	SOLVENT	ACID #	VISC.	VISC. Reduced	COLOR	Sward Hardness	NOTES
EPS 4401	50.0	7.45	Linseed	LAMS	3 max	Z+-Z4	N/A	6 max	60	<ul style="list-style-type: none"> Fast dry, hardness and abrasion resistance. Excellent for sealers and sports flooring. High gloss thru flat.
EPS 4408	60.0	7.70	Linseed	LAMS	2 max	Y-Z2	20s #4F @ 50%	6 max	60	<ul style="list-style-type: none"> Very fast dry and early hardness development. Sealers and sports flooring.
EPS 4429	60.0	7.67	Soya	LAMS	2 max	Z1-Z3	C-E @ 50%	6 max	50	<ul style="list-style-type: none"> Fast dry, abrasion resistance, less yellowing. High gloss thru flat.
EPS 4603	60.0	7.66	Soya	LAMS	3 max	U-V	N/A	6 max	44	<ul style="list-style-type: none"> Fast dry, hardness development, less yellowing. Low viscosity High gloss thru flats. Blending Vehicle for 350 VOC Varnish
EPS 4627	60.0	7.66	Mixed	LAMS	3 max	U-V	N/A	6 max	44	<ul style="list-style-type: none"> Fast dry with fast hardness development Low Viscosity High gloss thru flats Blending vehicle for 350 VOC varnish
EPS 4641	55.0	7.60	Soya	LAMS	4 max	X-Z1	C-F @ 48%	4 max	48	<ul style="list-style-type: none"> Fast dry, abrasion resistance and less yellowing Fast Viscosity reduction
EPS 4681	50.0	7.48	Soya	LAMS	2 max	Y-Z1	N-P @ 45%	4 max	60	<ul style="list-style-type: none"> Fast dry, and less yellowing. High Hardness Sealers and sports flooring. High gloss thru flat.

LAMS = Low Aromatic (<1%), Rule 66, Mineral Spirits

Questions? Call EPS Technical Service @ 1-800-601-8111

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.