



rev.04-21-08

## Urethane Resins for Wood Flooring & Clear Finishes

### LONG OIL ALKYDS FOR STAINS & URETHANE BLEND VEHICLES

| PRODUCT         | NVM   | WP<br>G | OIL<br>TYPE | SOLVENT         | ACID #  | VISC          | RED VISC  | COLOR  | NOTES   |
|-----------------|-------|---------|-------------|-----------------|---------|---------------|-----------|--------|---|
| <b>EPS 6603</b> | 70.0  | 8.00    | Soya        | Mineral spirits | 5 to 10 | Z2-Z4         | U-W @ 60% | 3 to 6 | Excellent flow & leveling, fast dry, durability           |
| <b>EPS 6677</b> | 100.0 | 8.30    | Linseed     | None            | 10 max  | W-Y           |           | 10 max | Excellent flow & leveling, wood penetration, solvent free |
| <b>EPS 6839</b> | 96.0  | 8.30    | Soya        | Xylene          | 5 to 10 | Z2-<br>Z3+1/2 | G-I @ 70% | 12 max | Excellent flow & leveling, low VOC,                       |

**Questions? Call EPS Technical Service @ 1-800-601-8111**

The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. EPS assumes no obligation or liability for use of this information. UNLESS EPS AGREES OTHERWISE IN WRITING, EPS MAKES NO WARRANTIES, EXPRESS OR IMPLIED, AND DISCLAIMS ALL IMPLIED WARRANTIES INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE OR FREEDOM FROM PATENT INFRINGEMENT. EPS WILL NOT BE LIABLE FOR ANY SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES. Your only remedy for any defect in this product is the replacement of the defective product, or a refund of its purchase price, at our option.